



LABORATORIO CERAMICO SEBASTIAN CARPI
COLEGIO OFICIAL DE INGENIEROS INDUSTRIALES DE CASTELLON

N.I.F: Q - 4670001 - I

AVENIDA DEL MAR, Nº 46 - 12003 CASTELLON
TEL: 964 208 583 - FAX: 964 202 594
www.laboratoriocarpi.com



TEST REPORT

PETITIONER: GRES DE LA MANCHA, S.L.

ADDRESS: Ctra. Consuegra, Km. 1,200

CITY: LOS YEBENES (Toledo)

TEST REPORT Nº: 51.278

PAGE Nº: 1 / 11

DATE OF TEST REPORT: 01/03/2012

DATE OF RECEIPT OF THE SAMPLE: 27/01/2012

DATE OF TESTS PERFORMANCE: 27/01 - 28/02/2012

NUMBER OF TILES SUPPLIED: 36

DESCRIPTION OF THE SAMPLE:

Ceramic tiles, single extruded, 299 x 604 mm, glazed. Ref.:

-- **BASE 30 x 60** --

Code lab.: 28-1-12

TEST PERFORMED:

- UNE-EN-ISO 10545-2 and ERRATUM: DETERMINATION OF DIMENSIONS AND SURFACE QUALITY.
- UNE-EN-ISO 10545-3 : DETERMINATION OF WATER ABSORPTION.
- UNE-EN-ISO 10545-4 : DETERMINATION OF MODULUS OF RUPTURE AND BREAKING STRENGTH.
- UNE-EN-ISO 10545-9 : DETERMINATION OF RESISTANCE TO THERMAL SHOCK.
- UNE-EN-ISO 10545-12 : DETERMINATION OF FROST RESISTANCE.

José A. Estibález Catalán
MANAGER

The samples and his description have been chosen by the petitioner.

The reported results relate only to the samples tested.

This report must not be reproduced in part without the written permission of Laboratory.

The uncertaintys have been evaluated according to recommendations of document ISO/TAG5/WGE : June 95.



LABORATORIO CERAMICO SEBASTIAN CARPI
COLEGIO OFICIAL DE INGENIEROS INDUSTRIALES DE CASTELLON

N.I.F: Q - 4670001 - I

AVENIDA DEL MAR, Nº 46 - 12003 CASTELLON
TEL: 964 208 583 - FAX: 964 202 594
www.laboratoriocarpi.com

Test report n°: 51.278

Page n°: 2 / 11

Petitioner: GRES DE LA MANCHA

Date: 01/03/2012

DETERMINATION OF DIMENSIONS
*** MEASUREMENTS OF LENGTH AND WIDTH ***

DESCRIPTION OF THE SAMPLE.-

Ceramic tiles, single extruded, 299 x 604 mm, glazed. Ref.:

-- **BASE 30 x 60** --

Code lab.: 28-1-12

RESULTS.- (Test performed after **UNE-EN-ISO 10545 Part 2 and Erratum:1998**)

* Work size: **604 mm x 299 mm**

Individuals measurements (mm)

<u>Tile</u>	<u>1</u>	<u>2</u>	<u>3</u>	<u>4</u>	<u>5</u>	<u>6</u>	<u>7</u>	<u>8</u>	<u>9</u>	<u>10</u>
<u>L1</u>	605.0	603.7	602.7	603.3	605.2	603.8	603.7	602.2	604.5	603.6
<u>L2</u>	602.6	604.2	603.3	603.3	602.5	603.8	603.3	603.6	603.6	603.7
<u>L3</u>	298.9	299.1	299.0	298.6	298.6	298.1	298.4	298.6	298.5	299.1
<u>L4</u>	298.9	298.6	298.5	299.2	298.7	298.7	298.8	298.8	299.2	298.4

Average measurements (mm)

<u>Length</u>	603.8	604.0	603.0	603.3	603.9	603.8	603.5	602.9	604.1	603.7
<u>Width</u>	298.9	298.9	298.8	298.9	298.7	298.4	298.6	298.7	298.9	298.8

Deviations from the work size (%)

<u>D^L_w</u>	-0.03	0.00	-0.17	-0.12	-0.02	-0.03	-0.08	-0.18	0.02	-0.05
<u>D^A_w</u>	-0.03	-0.03	-0.07	-0.03	-0.10	-0.20	-0.13	-0.10	-0.03	-0.07

Deviations from the average size of the sample (%)

<u>D^L_m</u>	0.03	0.07	-0.10	-0.05	0.05	0.03	-0.02	-0.12	0.08	0.02
<u>D^A_m</u>	0.03	0.03	0.00	0.03	-0.03	-0.13	-0.07	-0.03	0.03	0.00

* Average length of the sample: **603.6 mm**

* Average width of the sample: **298.8 mm**

* Maximum deviations of the average measurements from the work size: **0.02 % / -0.20 %**

* Maximum deviations of the average measurements from the average size of the sample:
0.08 % / -0.13 %

* Deviations uncertainty: **U= ± 0.03 % (k=2)**

Note: In calculating the deviations, the work size is assumed by the laboratory.



LABORATORIO CERAMICO SEBASTIAN CARPI
COLEGIO OFICIAL DE INGENIEROS INDUSTRIALES DE CASTELLON

N.I.F: Q - 4670001 - I

AVENIDA DEL MAR, Nº 46 - 12003 CASTELLON
TEL: 964 208 583 - FAX: 964 202 594
www.laboratoriocarpi.com

Test report n°: 51.278

Page n°: 3 / 11

Petitioner: GRES DE LA MANCHA

Date: 01/03/2012

DETERMINATION OF DIMENSIONS *** MEASUREMENTS OF THICKNESS ***

DESCRIPTION OF THE SAMPLE.-

Ceramic tiles, single extruded, 299 x 604 mm, glazed. Ref.:

-- **BASE 30 x 60** --

Code lab.: 28-1-12

RESULTS.- (Test performed after **UNE-EN-ISO 10545 Part 2 and Erratum:1998**)

* Work size thickness: **12.4 mm**

Measurements of thickness (mm)

<u>Tile</u>	<u>1</u>	<u>2</u>	<u>3</u>	<u>4</u>	<u>5</u>	<u>6</u>	<u>7</u>	<u>8</u>	<u>9</u>	<u>10</u>
G1	12.4	12.4	12.4	12.4	12.3	12.4	12.4	12.3	12.4	12.4
G2	12.4	12.4	12.3	12.3	12.4	12.3	12.3	12.4	12.2	12.4
G3	12.4	12.4	12.2	12.4	12.3	12.5	12.4	12.4	12.3	12.4
G4	12.3	12.4	12.3	12.3	12.2	12.4	12.4	12.3	12.5	12.3
Average thickness (mm)	12.4	12.4	12.3	12.4	12.3	12.4	12.4	12.4	12.4	12.4
Deviation from the work size thickness (%)	0.00	0.00	-0.81	0.00	-0.81	0.00	0.00	0.00	0.00	0.00

* Average thickness of the sample: **12.4 mm**

* Maximum deviation of the thickness from the work size thickness: **-0.81 %**

* Deviations uncertainty: **U = ± 0.81 % (k=2)**

Note: In calculating the deviations, the work size thickness is assumed to be equal to average thickness.



LABORATORIO CERAMICO SEBASTIAN CARPI
COLEGIO OFICIAL DE INGENIEROS INDUSTRIALES DE CASTELLON

N.I.F: Q - 4670001 - I

AVENIDA DEL MAR, Nº 46 - 12003 CASTELLON
TEL: 964 208 583 - FAX: 964 202 594
www.laboratoriocarpi.com

Test report n°: 51.278

Page n°: 4 / 11

Petitioner: GRES DE LA MANCHA

Date: 01/03/2012

DETERMINATION OF DIMENSIONS

*** MEASUREMENTS OF STRAIGHTNESS OF SIDES ***

DESCRIPTION OF THE SAMPLE.-

Ceramic tiles, single extruded, 299 x 604 mm, glazed. Ref.:

-- **BASE 30 x 60** --

Code lab.: 28-1-12

RESULTS.- (Test performed after **UNE-EN-ISO 10545 Part 2 and Erratum:1998**)

* Work size: **604 mm x 299 mm**

Measurements of straightness (mm)

<u>Tile</u>	<u>1</u>	<u>2</u>	<u>3</u>	<u>4</u>	<u>5</u>	<u>6</u>	<u>7</u>	<u>8</u>	<u>9</u>	<u>10</u>
R1	-0.29	-0.24	0.03	-0.34	-0.15	-0.37	-0.39	-0.28	-0.47	-0.29
R2	-0.25	-0.44	-0.27	-0.08	-0.37	-0.24	-0.24	0.04	-0.16	-0.46
R3	-1.00	0.01	0.11	-0.51	-0.89	-0.20	-0.57	0.14	-0.79	-0.14
R4	0.58	-0.32	-0.42	-0.16	0.38	-0.07	0.39	-0.63	0.36	-0.41

* Maximum deviation from straightness, related to the work size: **0.10 % / -0.17 %**

* Deviations uncertainty: **U= ± 0.03 % (k=2)**



LABORATORIO CERAMICO SEBASTIAN CARPI
COLEGIO OFICIAL DE INGENIEROS INDUSTRIALES DE CASTELLON

N.I.F.: Q - 4670001 - I

AVENIDA DEL MAR, Nº 46 - 12003 CASTELLON
TEL: 964 208 583 - FAX: 964 202 594
www.laboratoriocarpi.com

Test report n°: 51.278

Page n°: 5 / 11

Petitioner: GRES DE LA MANCHA

Date: 01/03/2012

DETERMINATION OF DIMENSIONS *** MEASUREMENTS OF RECTANGULARITY ***

DESCRIPTION OF THE SAMPLE.-

Ceramic tiles, single extruded, 299 x 604 mm, glazed. Ref.:

-- **BASE 30 x 60** --

Code lab.: 28-1-12

RESULTS.- (Test performed after **UNE-EN-ISO 10545 Part 2 and Erratum:1998**)

* Work size: **604 mm x 299 mm**

Measurements of rectangularity (mm)

<u>Tile</u>	<u>1</u>	<u>2</u>	<u>3</u>	<u>4</u>	<u>5</u>	<u>6</u>	<u>7</u>	<u>8</u>	<u>9</u>	<u>10</u>
O1	-1.95	0.28	1.36	0.09	-2.53	-0.33	0.15	2.98	-0.85	0.47
O2	2.90	0.03	0.58	-0.53	2.57	-0.96	0.45	-0.04	0.28	1.13
O3	0.96	-0.32	-0.72	0.23	1.31	0.49	0.09	-1.31	0.64	-0.50
O4	-1.41	0.30	-0.02	-0.05	-1.34	0.28	-0.30	-0.08	-0.38	-0.06

* Maximum deviation from rectangularity, related to the work size: **0.49 % / -0.47 %**

* Deviations uncertainty: **U= ± 0.03 % (k=2)**



LABORATORIO CERAMICO SEBASTIAN CARPI
COLEGIO OFICIAL DE INGENIEROS INDUSTRIALES DE CASTELLON

N.I.F: Q - 4670001 - I

AVENIDA DEL MAR, Nº 46 - 12003 CASTELLON
TEL: 964 208 583 - FAX: 964 202 594
www.laboratoriocarpi.com

Test report n°: 51.278

Page n°: 6/ 11

Petitioner: GRES DE LA MANCHA

Date: 01/03/2012

DETERMINATION OF DIMENSIONS

* MEASUREMENTS OF SURFACE FLATNESS *

DESCRIPTION OF THE SAMPLE.-

Ceramic tiles, single extruded, 299 x 604 mm, glazed. Ref.:

-- **BASE 30 x 60** --

Code lab.: 28-1-12

RESULTS.- (Test performed after **UNE-EN-ISO 10545 Part 2 and Erratum:1998**)

* Work size: **609 x 299 mm**

* Diagonal calculated from the work size: **674.0 mm**

Measurements of centre curvature (mm)

<u>Tile</u>	<u>1</u>	<u>2</u>	<u>3</u>	<u>4</u>	<u>5</u>	<u>6</u>	<u>7</u>	<u>8</u>	<u>9</u>	<u>10</u>
CC1	0.50	0.74	0.48	0.74	0.42	0.50	0.23	0.50	0.08	0.18
CC2	0.56	0.88	0.64	0.76	0.50	0.42	0.22	0.43	-0.01	0.34
CC3	0.42	0.33	0.17	0.51	0.53	0.53	0.15	0.37	0.20	0.34
CC4	0.41	0.37	0.26	0.52	0.50	0.56	0.21	0.38	0.23	0.38

Measurements of edge curvature (mm)

<u>Tile</u>	<u>1</u>	<u>2</u>	<u>3</u>	<u>4</u>	<u>5</u>	<u>6</u>	<u>7</u>	<u>8</u>	<u>9</u>	<u>10</u>
CL1	0.06	0.02	-0.24	-0.14	-0.15	0.04	0.01	-0.01	-0.04	-0.35
CL2	-0.16	-0.20	-0.07	0.00	0.01	-0.26	-0.29	-0.26	-0.28	-0.07
CL3	0.34	0.12	0.27	0.23	0.43	0.32	0.37	0.13	0.05	0.01
CL4	0.23	0.28	0.45	0.42	0.35	0.08	-0.01	0.50	0.20	0.17

Measurements of warpage (mm)

<u>Tile</u>	<u>1</u>	<u>2</u>	<u>3</u>	<u>4</u>	<u>5</u>	<u>6</u>	<u>7</u>	<u>8</u>	<u>9</u>	<u>10</u>
A1	0.02	0.69	0.27	0.28	-0.23	-0.10	-0.06	0.16	-0.48	-0.37
A2	0.04	0.86	0.68	0.29	-0.13	-0.37	-0.07	-0.08	-0.62	-0.13
A3	-0.21	-0.99	-0.84	-0.77	0.05	-0.02	-0.21	-0.24	0.16	0.01
A4	-0.34	-1.02	-0.65	-0.44	-0.04	0.03	-0.13	-0.10	0.38	-0.08

* Maximum centre curvature, related to the diagonal: **0.13 %**

* Maximum edge curvature, related to the work size: **0.08 / -0.12 %**

* Maximum warpage, related to the diagonal: **0.13 / -0.15 %**

* Deviations uncertainty: **U = ± 0.03 % (k=2)**

Note: In calculating the deviations, the work size is assumed by the laboratory.



LABORATORIO CERAMICO SEBASTIAN CARPI
COLEGIO OFICIAL DE INGENIEROS INDUSTRIALES DE CASTELLON

N.I.F: Q - 4670001 - I

AVENIDA DEL MAR, Nº 46 - 12003 CASTELLON
TEL: 964 208 583 - FAX: 964 202 594
www.laboratoriocarpi.com

Test report n°: 51.278

Page n° : 7 / 11

Petitioner: GRES DE LA MANCHA

Date: 01/03/2012

DETERMINATION OF SURFACE QUALITY

DESCRIPTION OF THE SAMPLE.-

Ceramic tiles, single extruded, 299 x 604 mm, glazed. Ref.:

-- **BASE 30 x 60** --

Code lab.: 28-1-12

RESULTS.- (Test performed after **UNE-EN-ISO 10545 Part 2 and Erratum:1998**)

* The number of tiles tested: **30 tiles.**

* The percentage of tiles without defects: **100 %**

* Observations: The tiles tested are free from visible defects.



LABORATORIO CERAMICO SEBASTIAN CARPI
COLEGIO OFICIAL DE INGENIEROS INDUSTRIALES DE CASTELLON

N.I.F: Q - 4670001 - I

AVENIDA DEL MAR, Nº 46 - 12003 CASTELLON
TEL: 964 208 583 - FAX: 964 202 594
www.laboratoriocarpi.com

Test report n°: 51.278

Page n°: 8 / 11

Petitioner: GRES DE LA MANCHA

Date: 01/03/2012

DETERMINATION OF WATER ABSORPTION

DESCRIPTION OF THE SAMPLE.-

Ceramic tiles, single extruded, 299 x 604 mm, glazed. Ref.:

-- **BASE 30 x 60** --

Code lab.: 28-1-12

RESULTS.- (Test performed after **UNE-EN-ISO 10545 Part 3:1997**)

* Water absorption for each tile (**Boiling method " E_b "**):

Tile	Water absorption (E_b) (%)
1	1.1
2	1.4
3	1.0
4	1.2
5	0.9

* Average water absorption of the sample: **1.1 %**

* Measurement uncertainty: **U = ± 0.2 % (k=2)**

* Average value uncertainty: **U = ± 0.3 % (k=2)**



LABORATORIO CERAMICO SEBASTIAN CARPI
COLEGIO OFICIAL DE INGENIEROS INDUSTRIALES DE CASTELLON

N.I.F: Q - 4670001 - I

AVENIDA DEL MAR, Nº 46 - 12003 CASTELLON
TEL: 964 208 583 - FAX: 964 202 594
www.laboratoriocarpi.com

Test report n°: 51.278

Page n°: 9 / 11

Petitioner: GRES DE LA MANCHA

Date: 01/03/2012

DETERMINATION OF MODULUS OF RUPTURE AND BREAKING STRENGTH

DESCRIPTION OF THE SAMPLE.-

Ceramic tiles, single extruded, 299 x 604 mm, glazed. Ref.:

-- **BASE 30 x 60** --

Code lab.: 28-1-12

RESULTS.- (Test performed after **UNE-EN-ISO 10545 Part 4:1997**)

* Parameters: L = 585 mm; l = 10 mm; t = 5 mm ; d = 20 mm

<u>Tile</u>	<u>Breaking load " F "</u> (N)	<u>Breaking strength " S "</u> (N)	<u>Modulus of rupture " R "</u> (N/mm ²)
1	1068.2	2096.3	25.5
2	1101.5	2159.5	25.8
3	1046.6	2053.3	25.0
4	1096.6	2152.0	25.7
5	1095.6	2149.4	26.2
6	1102.5	2162.1	26.3
7	1037.8	2036.6	24.8
Average	1078	2116	26

* Measurement uncertainty: **$U_F = 10.8 \text{ N}$** ; **$U_S = 21.0 \text{ N}$** ; **$U_R = 0.6 \text{ N/mm}^2$** (**k=2**)

* Average value uncertainty: **$U_F = 23 \text{ N}$** ; **$U_S = 46 \text{ N}$** ; **$U_R = 1 \text{ N/mm}^2$** (**k=2**)



LABORATORIO CERAMICO SEBASTIAN CARPI
COLEGIO OFICIAL DE INGENIEROS INDUSTRIALES DE CASTELLON

N.I.F: Q - 4670001 - I

AVENIDA DEL MAR, Nº 46 - 12003 CASTELLON
TEL: 964 208 583 - FAX: 964 202 594
www.laboratoriocarpi.com

Test report n°: 51.278
Page n°: 10 / 11
Petitioner: GRES DE LA MANCHA
Date: 01/03/2012

DETERMINATION OF RESISTANCE TO THERMAL SHOCK

DESCRIPTION OF THE SAMPLE.-

Ceramic tiles, single extruded, 299 x 604 mm, glazed. Ref.:

-- **BASE 30 x 60** --

Code lab.: 28-1-12

RESULTS.- (Test performed after Standard **UNE-EN-ISO 10545 Part 9:1997**)

- * Water absorption of the tiles: **Less than 10 %**
- * Type of test performed: **With immersion.**
- * Number of test specimens: **Five.**
- * Number of test specimens with visible defects: **Not - one.**
- * Observation: The tiles tested are free from visible defects.



LABORATORIO CERAMICO SEBASTIAN CARPI
COLEGIO OFICIAL DE INGENIEROS INDUSTRIALES DE CASTELLON

N.I.F: Q - 4670001 - I

AVENIDA DEL MAR, Nº 46 - 12003 CASTELLON
TEL: 964 208 583 - FAX: 964 202 594
www.laboratoriocarpi.com

Test report n°: 51.278

Page n°: 11 / 11

Petitioner: GRES DE LA MANCHA

Date: 01/03/2012

DETERMINATION OF FROST RESISTANCE

DESCRIPTION OF THE SAMPLE.-

Ceramic tiles, single extruded, 299 x 604 mm, glazed. Ref.:

-- **BASE 30 x 60** --

Code lab.: 28-1-12

RESULTS.- (Test performed after **UNE-EN-ISO 10545 Part 12:1997**)

* Number of tiles tested: **Ten.**

* Method used to impregnate the tiles: **Impregnation with water at pressure below of the atmospheric pressure.**

* The initial water content before the freeze-thaw test: **$E_1 = 0.7 \% \pm 0.1 \%$** (**k=2**)

* The final water content after the freeze-thaw test: **$E_2 = 3.0 \% \pm 0.2 \%$** (**k=2**)

* Number of damaged tiles after 100 cycles: **Not-one.**

* Description of defects after the freeze-thaw test: The tiles tested are free from visible defects.
