



LABORATORIO CERAMICO SEBASTIAN CARPI
COLEGIO OFICIAL DE INGENIEROS INDUSTRIALES DE CASTELLON

N.I.F: Q - 4670001 - I

AVENIDA DEL MAR, Nº 46 - 12003 CASTELLON
TEL: 964 208 583 - FAX: 964 202 594
www.laboratoriocarpi.com



TEST REPORT

PETITIONER: GRES DE LA MANCHA, S.L.

ADDRESS: Ctra. Consuegra, Km. 1,200

CITY: LOS YEBENES (Toledo)

TEST REPORT Nº: 51.289

PAGE Nº: 1 / 2

DATE OF TEST REPORT: 01/03/2012

DATE OF RECEIPT OF THE SAMPLE: 27/01/2012

DATE OF TESTS PERFORMANCE: 27/01 - 28/02/2012

NUMBER OF TILES SUPPLIED: 7

DESCRIPTION OF THE SAMPLE:

Ceramic tiles, double extruded, 245 mm x 245 mm, glazed. Ref.:

-- **Serie ASPER RODAMANTO** --

Code lab.: 28-12-12

TEST PERFORMED:

- UNE-ENV 12633 : DETERMINATION OF UNPOLISHED FLOORS SLIP RESISTANCE .

José A. Estibález Catalán
MANAGER

The samples and his description have been chosen by the petitioner.

The reported results relate only to the samples tested.

This report must not be reproduced in part without the written permission of Laboratory.

The uncertaintys have been evaluated according to recommendations of document ISO/TAG5/WGE : June 95.



LABORATORIO CERAMICO SEBASTIAN CARPI
COLEGIO OFICIAL DE INGENIEROS INDUSTRIALES DE CASTELLON

N.I.F: Q - 4670001 - I

AVENIDA DEL MAR, Nº 46 - 12003 CASTELLON
TEL: 964 208 583 - FAX: 964 202 594
www.laboratoriocarpi.com

Test report n°: 51.289

Page n°: 2 / 2

Petitioner: GRES DE LA MANCHA

Date: 01/03/2012

DETERMINATION OF SLIP RESISTANCE (PENDULUM)

DESCRIPTION OF THE SAMPLE.-

Ceramic tiles, double extruded, 245 mm x 245 mm, glazed. Ref.:

-- **Serie ASPER RODAMANTO** --

Code lab.: 28-12-12

RESULTS.- (Test performed after the **UNE-ENV 12633:2003: Annex A**)

<u>Specimen</u>	<u>Slip resistance</u> (R_d)
1	69
2	68
3	68
4	70

* Average slip resistance: **R_d = 69**

* Average value uncertainty: **U = ± 5 (k=2)**

* Observations.- The classification established on the **SU1** document (Safety of fall risks) of the Technical Code of Building, approved to R.D. 314/2006, is the next:

<u>CLASSIFICATION OF FLOORS AFTER "SU1"</u>	
<u>Slip resistance</u> (R_d)	<u>Class</u>
R _d ≤ 15	Class 0
15 < R _d ≤ 35	Class 1
35 < R _d ≤ 45	Class 2
R _d > 45	Class 3