



LABORATORIO CERAMICO SEBASTIAN CARPI
COLEGIO OFICIAL DE INGENIEROS INDUSTRIALES DE CASTELLON

N.I.F: Q - 4670001 - I

AVENIDA DEL MAR, Nº 46 - 12003 CASTELLON
TEL: 964 208 583 - FAX: 964 202 594
www.laboratoriocarpi.com



TEST REPORT

PETITIONER: GRES DE LA MANCHA, S.L.

ADDRESS: Ctra. Consuegra, Km. 1,200

CITY: LOS YEBENES (Toledo)

TEST REPORT Nº: 51.283

PAGE Nº: 1 / 2

DATE OF TEST REPORT: 01/03/2012

DATE OF RECEIPT OF THE SAMPLE: 27/01/2012

DATE OF TESTS PERFORMANCE: 27/01 - 28/02/2012

NUMBER OF TILES SUPPLIED: 16

DESCRIPTION OF THE SAMPLE:

Ceramic tiles, double extruded, 245 mm x 245 mm, glazed. Ref.:

-- **Serie RODAMANTO** --

Code lab.: 28-6-12

TEST PERFORMED:

- UNE-EN-ISO 10545-7 : DETERMINATION OF RESISTANCE TO SURFACE ABRASION.
GLAZED TILES.

José A. Estibález Catalán
MANAGER

The samples and his description have been chosen by the petitioner.

The reported results relate only to the samples tested.

This report must not be reproduced in part without the written permission of Laboratory.

The uncertaintys have been evaluated according to recommendations of document ISO/TAG5/WGE : June 95.



LABORATORIO CERAMICO SEBASTIAN CARPI
COLEGIO OFICIAL DE INGENIEROS INDUSTRIALES DE CASTELLON

N.I.F: Q - 4670001 - I

AVENIDA DEL MAR, Nº 46 - 12003 CASTELLON
TEL: 964 208 583 - FAX: 964 202 594
www.laboratoriocarpi.com

Test report n°: 51.283
Page n°: 2 / 2
Petitioner: GRES DE LA MANCHA
Date: 01/03/2012

DETERMINATION OF RESISTANCE TO SURFACE ABRASION
*** GLAZED TILES ***

DESCRIPTION OF THE SAMPLE.-

Ceramic tiles, double extruded, 245 mm x 245 mm, glazed. Ref.:

-- **Serie RODAMANTO** --

Code lab.: 28-6-12

RESULTS.- (Test performed after **UNE-EN-ISO 10545 Part 7:1999**)

* Classification: **Class 2**

* Abrasion stage at which visual failure occurred: **600 revolutions.**
